

Product Information Sheet

Name: Open Cell Packaging Foam

	Charcoal Firm	Charcoal Regular
Density (lbs./cubic ft)	1.70-1.90	1.40-1.60
25% IFD (pounds)	80-90	45-55
Support Factor (65% / 25%) Min.	1.9	1.9
Tensile (PSI) Min.	14	12
Elongation (%) Min.	200	200
Tear (PPI) Min.	1.4	1.2
Resiliency (%) Min.	30	35
Flammability	FMVSS No. 302 Contains Fire Retardant Additives	CAL 117-2013

All testing is done by the ASTM D 3574 Standard

Note 1: The Cal 117-2013 Smolder test is not intended to predict performance presented by this material under actual fire conditions.

Note 2: Cal 117, Biocide, and Air Flow results are only guaranteed at time of shipment.

Note 3: All polyurethane foam used by Foam N' More is guaranteed latex free. Only "F" and "FB" grades contain fire retardant.

Results relate only to items tested. Specifications may be changed at the discretion of Foam N' More without prior notification.

Foam N' More Inc reserves the right to alter the specifications of the above products at any time without prior notification.